

## Abstract

There is provided an adhesive film comprising:

(i) a substrate layer, which comprises a thermoplastic resin, and

5 (ii) an adhesive layer, which comprises an olefin copolymer, wherein the olefin copolymer comprises polymerization units of at least two olefins selected from the group consisting of ethylene and  $\alpha$ -olefins having 3 to 20 carbon atoms, and the olefin copolymer satisfies the requirements:

10 (a) the olefin copolymer has neither a peak of crystal melting calorie of not less than 1 J/g, nor a peak of crystallization calorie of not less than 1 J/g in a differential scanning calorimetry according to JIS K 7122, and

(b) a molecular weight distribution of the olefin  
15 copolymer,  $M_w/M_n$ , is not more than 3.